

# EPDM Hose 15

EPDM hose

**Bredel**

Hose Pumps

## Features and benefits

- Tight tolerances for low stress on bearings
- Perfect compression for long life
- Excellent suction performance – 9 m suction lift
- High pressure capability – up to 145 psi
- Repeatable volumetric accuracy to  $\pm 1\%$
- Max. fluid temperature: 176 °F Min. fluid temperature: 14 °F



## Technical specifications

	EPDM Hose 15
Max. operating pressure	10 bar
Max. operating pressure	145 psi
Max. suction capability	9 mWC
Max. suction capability	354 inWC
Suction capability (80% Flow rate)	8.5 mWC
Suction capability (80% Flow rate)	335 inWC
Operating temperature range	-20 to 45 °C
Operating temperature range	-4 to 113 °F
Fluid temperature range	-10 to 80 °C
Fluid temperature range	14 to 176 °F
Bore size	15 mm
Bore size	0.59 in
Wall thickness	10.5 mm
Wall thickness	0.413 in
Length	755 mm
Length	29.7 in
Weight	0.8 kg
Weight	1.76 lbs

Your local Bredel sales office/distributor can advise the right hose for your application. For best pump performance use Bredel Genuine Hose Lubricant (NSF Non food Compound Program Listed, category H1)

## Materials of construction


	EPDM Hose 15
Material	EPDM
Inner layer	EPDM
Outer layer	NR

## Hose composition



1. Rough hose surface prior to machining.
2. Precision machined NR outer layer.
3. Two or four nylon cord reinforcement layers.
4. Inner layer available in NR, EPDM, NBR, F-NBR or CSM.

## Product codes



Label codes	
A	Pump type
B	Re-order number
C	Bore size
D	Material of the inner layer
E	Maximum permitted pressure
F	Factory code [material; year; month]

On one end of each hose the factory code [material; year; month] and the batch number are engraved.

Year: last digit (7 = 2017)

Month: A = Jan, E = May

Material: E = F-NBR, M = CSM, NM or NT = NR, P = NBR, S = EPDM

---

Disclaimer: The information contained in this document is believed to be correct at the time of publication, but Watson-Marlow Bredel BV accepts no liability for any error it contains, and reserves the right to alter specifications without prior notice. All mentioned values in this document are values under controlled circumstances at our test bed. Actual flow rates achieved may vary because of changes in temperature, viscosity, inlet and discharge pressures and/or system configuration. APEX, DuCoNite, Bioprene and Bredel are registered trademarks.

*[wmfts.com/global](https://wmfts.com/global)*



01 May 2024